

SCALECOLOR  
ARTIST  
NEW COLORS!



COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
SART 49	CORK BROWN	PY-42	SYNTHETIC YELLOW IRON OXIDES	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
		PBk-11	MARS BLACK			
SART 50	PASTEL PINK	PR-122	QUINACRIDONE MAGENTA	HIGH	7-8 HIGH	HIGH
		PW-6	TITANIUM DIOXIDE		8 HIGH	
SART 51	PALE SKIN	PR-112	NAPHTHOL RED	MEDIUM	7 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES		8 HIGH	
		PW-6	TITANIUM DIOXIDE			
SART 52	SKY BLUE	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	
		PW-6	TITANIUM DIOXIDE			
SART 53	COBALT VIOLET GREY	PBk-11	MARS BLACK	HIGH	8 HIGH	HIGH
		PV-23	DIOXAZINE VIOLET			
		PB-15:3	PHTHALOCYANINE BLUE			
SART 54	BURGUNDY WINE RED	PR-112	NAPHTHOL RED	MEDIUM	7 HIGH	HIGH
		PV-23	DIOXAZINE VIOLET		8 HIGH	
		PBk-11	MARS BLACK			
SART 55	LEMON YELLOW	PY-3	HANSA YELLOW 10 G	HIGH	6-7 MEDIUM	MEDIUM
SART 56	YELLOW OXIDE	PY-83	DIARYLIDE YELLOW	MEDIUM	5-6 MEDIUM	MEDIUM
		PR-101	SYNTHETIC RED IRON OXIDE		8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			

COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
<b>SART 57</b>	PERMANENT ORANGE	PO-73	SYNTHETIC ORANGE	HIGH	8 HIGH	HIGH
<b>SART 58</b>	CORAL RED	PR-112	NAPHTHOL RED	HIGH	7 HIGH	HIGH
		PO-5	MONOAZO ORANGE		7-8 HIGH	
		PR-122	QUINACRIDONE MAGENTA			
<b>SART 59</b>	VIOLET	PV-23	DIOXAZINE VIOLET	HIGH	8 HIGH	HIGH
		PV-19	QUINACRIDONE RED		7-8 HIGH	
<b>SART 60</b>	TITANIUM GREY	PO-5	MONOAZO ORANGE	HIGH	7 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES		8 HIGH	
		PBk-11	MARS BLACK			
<b>SART 61</b>	LIME GREEN	PY-3	HANSA YELLOW 10 G	HIGH	6-7 MEDIUM	MEDIUM
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	HIGH
<b>SART 62</b>	ALIZARIN GREEN	PY-3	HANSA YELLOW 10 G	HIGH	6-7 MEDIUM	MEDIUM
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	HIGH
		PY-42	SYNTHETIC YELLOW IRON OXIDE		7-8 HIGH	
		PB-15:3	PHTHALOCYANINE BLUE			
<b>SART 63</b>	JADE GREEN	PG-7	PHTHALOCYANINE GREEN	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
<b>SART 64</b>	TURQUOISE	PG-7	PHTHALOCYANINE GREEN	HIGH	8 HIGH	HIGH
		PB-15:3	PHTHALOCYANINE BLUE		7-8 HIGH	
<b>SART 65</b>	OXFORD BLUE	PB-29	ULTRAMARINE BLUE	HIGH	6-7 MEDIUM	MEDIUM
		PV-23	DIOXAZINE VIOLET		8 HIGH	HIGH
		PBk-11	MARS BLACK			
<b>SART 66</b>	DARK PRUSSIAN BLUE	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	
		PV-23	DIOXAZINE VIOLET			
<b>SART 67</b>	NEON ORANGE	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
		PO-71	SYNTHETIC ORGANIC ORANGE		8 HIGH	HIGH

COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
SART 68	NEON PINK	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
SART 69	NEON RED	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
		PR-112	NAPHTHOL RED		7 HIGH	HIGH
SART 70	NEON YELLOW	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
SART 71	NEON GREEN	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
SART 72	NEON BLUE	PF	FLUORESCENT	MEDIUM	6-7 MEDIUM	MEDIUM
SART 73	YELLOW INK	PY 154	BENZIMIDAZOLONE	MEDIUM	6-7 MEDIUM	MEDIUM
SART 74	RED INK	PR 2	NAPHTHOL RED	MEDIUM	6-7 MEDIUM	MEDIUM
SART 75	BLUE INK	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
SART 76	GREEN INK	PG-7	PHTHALOCYANINE GREEN	HIGH	8 HIGH	HIGH
		PY 14	DIARYLIDE YELLOW	MEDIUM	6-7 MEDIUM	MEDIUM
SART 77	ORANGE INK	PO 13	BENZIDINE ORANGE	MEDIUM	6-7 MEDIUM	MEDIUM
SART 78	VIOLET INK	PW-6	TITANIUM DIOXIDE	HIGH	8 HIGH	HIGH
		PV-23	DIOXAZINE VIOLET		7-8 HIGH	
		PV-19	QUINACRIDONE RED		8 HIGH	
SART 79	BLACK INK	PBk-7	CHARCOAL BLACK	HIGH	8 HIGH	HIGH
SART-80	WHITE INK	PW-6	TITANIUM DIOXIDE	HIGH	8 HIGH	HIGH
SART 81	CRIMSON INK	PR-57:1	SYNTHETIC ORGANIC RUBY	MEDIUM	6-7 MEDIUM	MEDIUM
SART 82	PISTACHIO GREEN INK	PG-7	PHTHALOCYANINE GREEN	HIGH	8 HIGH	HIGH
		PY-3	HANSA YELLOW 10 G		6-7 MEDIUM	MEDIUM
SART 83	TURQUOISE INK	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	
SART 84	CHESTNUT INK	PY-42	SYNTHETIC YELLOW IRON OXIDES	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES		6-7 MEDIUM	MEDIUM
		PY 14	DIARYLIDE YELLOW		8 HIGH	HIGH

SCALECOLOR  
ARTIST  
CLASSIC RANGE



COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
<b>SART 01</b>	ART WHITE	PW-6	TITANIUM DIOXIDE	MEDIUM	8 HIGH	HIGH
<b>SART 02</b>	ART BLACK	PBk-7	CARBON BLACK	HIGH	8 HIGH	HIGH
<b>SART 03</b>	PRIMARY BLUE	PB-15:3	PHthalOCYANINE BLUE	MEDIUM	7-8 HIGH	HIGH
<b>SART 04</b>	PRIMARY YELLOW	PY-14	DIAZO, TOLUIDINE	MEDIUM	6-7 MEDIUM	MEDIUM
<b>SART 05</b>	PRIMARY RED	PR-112	NAPHTOL RED	MEDIUM	7 HIGH	HIGH
<b>SART 06</b>	BURNT SIENNA UMBER	PBr-7	SYNTHETIC IRON OXIDES	HIGH	8 HIGH	HIGH
		PY-42	SYNTHETIC IRON YELLOW OXIDE			
<b>SART 07</b>	PINK FLESH	PR-101	SYNTHETIC IRON RED OXIDE	HIGH	8 HIGH	HIGH
		PW-6	TITANIUM DIOXIDE			
<b>SART 08</b>	GOLDEN FLESH	PY-42	SYNTHETIC IRON YELLOW OXIDE	MEDIUM	8 HIGH	HIGH
		PO-5	MONO-AZOIC ORANGE		7 HIGH	
<b>SART 09</b>	LIGHT SKIN	PW-6	TITANIUM DIOXIDE	MEDIUM	7-8 HIGH	HIGH
		PY-42	SYNTHETIC IRON YELLOW OXIDE		8 HIGH	
<b>SART 10</b>	CRIMSON	PV-19	QUINACRIDONE RED	MEDIUM	7-8 HIGH	HIGH

COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
SART 11	MOSS GREEN	PY-14	DIAZO, TOLUIDINE	HIGH	6-7 MEDIUM	MEDIUM
		PY-42	SYNTHETIC IRON YELLOW OXIDE		8 HIGH	
SART 12	BURNT SKIN	PBr-7	SYNTHETIC IRON OXIDES	HIGH	8 HIGH	HIGH
		PY-42	SYNTHETIC IRON YELLOW OXIDE			
SART 13	BUFF	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBk-11	MARS BLACK			
SART 14	PEARL GREY	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBk-11	MARS BLACK			
SART 15	VIOLET GREY	PB-29	ULTRAMARINE BLUE	HIGH	6-7 MEDIUM	MEDIUM
		PV-15	ULTRAMARINE VIOLET			
SART 16	GREEN GREY	PB-29	ULTRAMARINE BLUE	HIGH	6-7 MEDIUM	MEDIUM
		PV-15	ULTRAMARINE VIOLET			
SART 17	VANILLA YELLOW	PY-53	NICKEL ANTIMONY TITANIUM YELLOW RUTILE	MEDIUM	8 HIGH	HIGH
		PY-14	DIAZO, TOLUIDINA		6-7 MEDIUM	
SART 18	YELLOW NAPLES	PY-3	HANSA YELLOW 10 G	HIGH	6-7 MEDIUM	MEDIUM
		PO-5	MONO-AZOIC ORANGE		7 HIGH	
SART 19	INTENSE YELLOW	PY-3	HANSA YELLOW 10 G	MEDIUM	6-7 MEDIUM	MEDIUM
		PY-83	DIARYLIDE YELLOW		5-6 MEDIUM	
SART 20	YELLOW OCHRE	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 21	RAW SIENNA	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 22	ORANGE	PR-112	NAPHTOL RED	MEDIUM	7 HIGH	HIGH
		PO-5	MONO-AZOIC ORANGE			
SART 23	MAGENTA	PR-122	QUINACRIDONE MAGENTA	MEDIUM	7-8 HIGH	HIGH
SART 24	PURPLE	PV-23	DIOXAZINE VIOLET	HIGH	7-8 HIGH	HIGH
		PR-122	QUINACRIDONE MAGENTA			

COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
SART 25	DARK VIOLET	PR-146	NAPHTHOL RED AS	HIGH	6 MEDIUM	MEDIUM
		PR-122	QUINACRIDONE MAGENTA		7-8 HIGH	HIGH
SART 26	TURQUOISE BLUE	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	
SART 27	COBALT BLUE	PB-15:1	PHTHALOCYANINE BLUE RS	HIGH	7-8 HIGH	HIGH
SART 28	LIGHT ULTRAMARINE	PB-29	ULTRAMARINE BLUE	MEDIUM	6-7 MEDIUM	MEDIUM
		PV-15	ULTRAMARINE VIOLET			
SART 29	DARK ULTRAMARINE	PB-29	ULTRAMARINE BLUE	MEDIUM	6-7 MEDIUM	MEDIUM
		PV-15	ULTRAMARINE VIOLET			
SART 30	PRUSIAN BLUE	PB-15:3	PHTHALOCYANINE BLUE	HIGH	7-8 HIGH	HIGH
		PBk-7	CARBON BLACK		8 HIGH	
SART 31	LIGHT MOSS GREEN	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN			
SART 32	SPRING GREEN	PY-83	DIARYLIDE YELLOW	MEDIUM	5-6 MEDIUM	MEDIUM
		PG-7	PHTHALOCYANINE GREEN		8 HIGH	HIGH
SART 33	EMERALD GREEN	PG-7	PHTHALOCYANINE GREEN	MEDIUM	8 HIGH	HIGH
		PB-15:1	PHTHALOCYANINE BLUE RS		7-8 HIGH	
SART 34	SAP GREEN	PG-7	PHTHALOCYANINE GREEN	HIGH	8 HIGH	HIGH
SART 35	OLIVE GREEN	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 36	EARTH GREEN	PY-42	SYNTHETIC IRON YELLOW OXIDE	MEDIUM	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 37	RED OCHRE	PBr-7	SYNTHETIC IRON OXIDES	HIGH	8 HIGH	HIGH
		PR-101	SYNTHETIC IRON RED OXIDE			
SART 38	BURNT UMBER	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			

COLOR	COLOR NAME	COLOR INDEX	CHEMICAL NAME	HIDING POWER	LIGHTFASTNESS	FASTNESS
SART 39	WOOD	PR-101	SY	HIGH	8 HIGH	HIGH
		PBk-11	MARS BLACK			
SART 40	RAW UMBER	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 41	DARK BROWN OCHRE	PBk-11	MARS BLACK	HIGH	8 HIGH	HIGH
		PV-19	QUINACRIDONE RED		7-8 HIGH	
SART 42	BURNT SIENNA	PY-42	SYNTHETIC IRON YELLOW OXIDE	HIGH	8 HIGH	HIGH
		PBr-7	SYNTHETIC IRON OXIDES			
SART 44	ARTIC BLUE	PB-29	ULTRAMARINE BLUE	HIGH	6-7 MEDIUM	MEDIUM
		PV-15	ULTRAMARINE VIOLET			
SART 45	PASTEL VIOLET	PV-19	QUINACRIDONE RED	MEDIUM	7-8 HIGH	HIGH
		PV-23	DIOXAZINE VIOLET			
SART 46	PASTEL GREEN	PBK-11	MARS BLACK	HIGH	8 HIGH	HIGH
		PG-7	PHTHALOCYANINE GREEN			
SART 47	OFF WHITE	PY-42	SYNTHETIC IRON YELLOW OXIDE	MEDIUM	8 HIGH	HIGH
		PBk-11	MARS BLACK			
SART 48	PASTEL BLUE	PB-15:1	PHTHALOCYANINE BLUE RS	HIGH	7-8 HIGH	HIGH HIGH
		PBk-7	CARBON BLACK		8 HIGH	